



15 rue des Frères Lumière – BP 136
78374 PLAISIR
FRANCE

Tél : 01.30.80.81.98

Fax : 01.30.80.81.99

WEB : www.babbco.fr

E-MAIL : sherwinbabbco@orange.fr

TECHNICAL

DATA SHEET

Ref : TDS/ B 104A

Page : 1/2

Rev : 4 Date : 11/09

WHITE CONTRAST PAINT FOR MPI B 104A

MANUFACTURER : Babb Co (FR)

DESCRIPTION / APPLICATION(S) :

Very fast drying, high opacity white contrast paint. Improves performance of any black magnetic detecting medium.

May be used in any MPI (Magnetic Particle Inspection) technique : current flow, electromagnets, permanent magnets, etc...

Companion products : B 103C, B 105, KP42, WCB 42

SPECIFICATION(S) / STANDARD(S) :

- Conforms to code(s) : ASME, RCC-M
standard(s) : ISO 9934-2
NFF 00-090
specification(s):ASTM-E-1444
- Homologation : PMUC (French acronym for : Products and Equipments allowed for use in power plants by EDF-French Electricity Board)

PHYSICO-CHEMICAL PROPERTIES:

- Highly volatile and low toxicity propelling agent
- Halogenous content (Chlorine + Fluorine + Bromine) : < 200 ppm
- Sulfur content : < 200 ppm


PACKAGING / TRANSPORT / STORAGE :

.Packaging : spraycan 500mL

.Transport / Handling : Refer to Material Safety Data Sheet (MSDS).

.Storage / Shelf life : Keep away from moisture
Temperature range : -5°C à 50° C (23°F to 122°F).
Keep packaging closed after taking out some of the product

Spraycan : 30 months

 <p>15 rue des Frères Lumière – BP 136 78374 PLAISIR FRANCE Tél : 01.30.80.81.98 Fax : 01.30.80.81.99 WEB : www.babbco.fr E-MAIL : sherwinbabbco@orange.fr</p>	<p>TECHNICAL DATA SHEET</p>	<p>Ref : TDS/ B 104A</p> <p>Page : 2/2</p> <p>Rev : 4 Date : 11/09</p>
---	--	--

INSTRUCTIONS :

If necessary remove scale, paint residue, oxide, etc...

Degrease using cleaner N 120 and cleaning rags or preimpregnated N 120 swabs

Strongly shake B 104A spray can, then, from a distance of 20 to 30 cm, firmly push nozzle while keeping spray can upside.

Spray a thin, uniform coat of B 104A (if possible only one layer)

A 20 to 30 µm layer is enough. Too a thick coat leads to coat defects ("orange skin") and decreases inspection sensitivity.

B 104A is not soluble in water or in currently used hydrocarbon-based magnetic inks.

After inspection, special solvent B 105 shall be used to remove B 104A.

HEALTH AND SAFETY : Refer to Material Safety Data Sheet (MSDS).

The information given herein is given in good faith to our customers for the sole purpose of assisting them in the use of the products. The document contains no formal or implicit guarantee regarding its use.

Babb Co cannot be held responsible for damages of any nature resulting from information provided in this document. In addition, none of the information which the document contains should be interpreted as a recommendation for the use of the products which would infringe the protected rights of industrial property.