 <p>15 Rue des Frères Lumière – BP 136 78374 PLAISIR FRANCE Pho : +33(0)1.30.80.81.98 Fax : +33(0)1.30.80.81.99 WEB : <a href="http://www.babbco.fr">www.babbco.fr</a> E-MAIL : <a href="mailto:sherwinbabbco@wanadoo.fr">sherwinbabbco@wanadoo.fr</a></p>	<p><b>TECHNICAL DATA SHEET</b></p>	<p>Ref : <b>FT/R62</b></p> <p>Page : 1/2</p> <p>Rev : 0 Date : 02/04</p>
---	--	--

**QUICK DRYING NON-AQUEOUS WET DEVELOPER R 62**

**MANUFACTURER : BABB CO**

**DESCRIPTION / USE :**

Solvent based developer used to help detect and enhance indications from red dye or fluorescent penetrants, in low or normal temperature conditions.

. Companion product(s) : Any penetrant.

**SPECIFICATION(S) / STANDARD(S) :**

French Electricity Board (EDF) RCC-M Code.  
ASME Code. ISO 3452-2 form d.

**DATA :**


Aspect : white power in suspension in a colorless solvent  
Flash point : < 0°C (+32°F)  
Sensitivity : > 75 % on 30 µm Nichrome Test Panels

Very low in halogens and sulphur.

Compatible with all metals and ceramics, and some synthetic materials.

**PACKAGING/TRANSPORT/STORAGE :**

- . Packaging : 5 L, 10 L polythen can.  
300 mL spray can.
- . Transport / Handling : refer to MSDS (materials safety data sheet)
- . Storage / Shelf life : Keep away from moisture  
Temperature range : 0 to + 50° C. (32° F to 120° F)  
Keep cans tightly closed.  
Polythen cans : 48 months  
Spray can : 48 months

 <p>15 Rue des Frères Lumière – BP 136 78374 PLAISIR FRANCE Pho : +33(0)1.30.80.81.98 Fax : +33(0)1.30.80.81.99 WEB : <a href="http://www.babbco.fr">www.babbco.fr</a> E-MAIL : <a href="mailto:sherwinbabbco@wanadoo.fr">sherwinbabbco@wanadoo.fr</a></p>	<h1>TECHNICAL DATA SHEET</h1>	Ref : <b>FT/R62</b>  Page : 2/2  Rev : 0 Date : 02/04
---	-----------------------------------	---

## **INSTRUCTIONS :**

After removal of the excess of penetrant as per recommended means (refer to Operation section of penetrants Technical Data Sheets) and drying of the parts, apply developer only by spraying from a spray can or a pneumatic spray gun. Any other means is not recommended.

Application shall give an even, very light coating. It is better to apply two very thin layers than only one which may be too thick.

### **Inspection :**

Generally within 10 to 30 minutes after solvent has evaporated.

It is a good habit to check surface while developer is sprayed : fading indications may show up for some few seconds and not reappear when developer is dry.

If particularly tight indications are suspected, wait for as long as 2 hours before inspection.

### **Cleaning :**

R 62 developer is very easily removed with a clean rag, or by water rinsing.

## **HEALTH AND SAFETY :** refer to MSDS.

*The information given herein is given in good faith to our customers for the sole purpose of assisting them in the use of the products. The document contains no formal or implicit guarantee regarding its use.*

*Babb Co cannot be held responsible for damages of any nature resulting from information provided in this document. In addition, none of the information which the document contains should be interpreted as a recommendation for the use of the products which would infringe the protected rights of industrial property.*